

⑨ 日本国特許庁 (JP)

⑩ 特許出願公開

⑫ 公開特許公報 (A)

昭59—85729

⑪ Int. Cl.³
B 29 F 1/00

識別記号

庁内整理番号
8016—4F

⑬ 公開 昭和59年(1984)5月17日

発明の数 1
審査請求 未請求

(全 3 頁)

⑭ プランジャブリブラ式射出成形機

番地三菱重工業株式会社名古屋
機器製作所内

⑯ 特 願 昭57—195730

⑰ 出 願 人 三菱重工業株式会社

⑱ 出 願 昭57(1982)11月8日

東京都千代田区丸の内2丁目5

⑲ 発 明 者 石川絃一

番1号

名古屋市中村区岩塚町字高道1

⑳ 復 代 理 人 弁理士 唐木貴男 外1名

明 細 書

1. 発明の名称 プランジャブリブラ式射出成形機

2. 特許請求の範囲

プランジャブリブラ式射出成形機の押出機ユニットにおいて、スクリュ先端及びスクリュバレル先端部にスロットル部の隙間を構成して、押出機先端部にスクリュ背圧を発生させると共に、同スクリュを軸方向に移動させる手段を設けて、前記スクリュ背圧を調整可能にしたことを特徴とするプランジャブリブラ式射出成形機。

3. 発明の詳細な説明

可塑化する樹脂に十分な練りを与える為、押出機先端にある樹脂に或る一定の圧力が発生する様にさせることがある(圧力0~300 kg/cm²程度)。圧力を発生させる場合、従来一般的には第1図におけるプランジャバレル(1)の内部の圧力が高くなる様、射出シリンダ(2)内の油圧をコントロールする。

ここで第1図について作動を説明すると、ホツバ(7)内の原料はモータ(6)によつて駆動される押出スクリュバレル(8)内の押出スクリュ(9)で可塑化され、搬送される。また樹脂の混練を良くする為にスクリュ背圧を加えるには、射出シリンダ(2)の空間Aに僅かに油圧を加えて可塑化を行なえばよい。この時押出スクリュ(9)の先端、ストツババルブ(3)、プランジャバレル(1)内の空間Cには、0~300 kg/cm²の圧力が発生している。

しかしながら従来の第1図のものには次のような欠点があつた。即ち、可塑化中にプランジャバレル(1)内の樹脂圧を上げる為、樹脂がストツババルブ(3)、射出プランジャ(4)とプランジャバレル(1)の隙間といった場所で発生すること、また可塑化中に型を開く場合、ノズル(5)にストツババルブ(3)の機能を与えておかないと、金型内に樹脂が流れ込み、全自動運転の場合次のサイクルの成形がうまく行かない等の欠点があつた。

本発明は前記従来の欠点を解消するために提案されたもので、樹脂流れや、金型内への樹脂の流れ

れ込みを生ぜずスクリュ背圧を生ぜしめ、樹脂に十分な混練を与えることを目的としたものであり、スクリュ背圧を押出機先端部で発生させること、及び圧力を発生させる為に、スクリュ及びスクリュバレルの先端の形状をスロットルバルブ構造にするとともに、スクリュ背圧を自由に調整出来る様にするために、スクリュを軸方向に移動可能にするようにしたプランジャブリブラ式射出成形機を提供せんとするものである。

以下本発明の実施例を図面について説明すると、第2図は本発明の実施例を示し、(1)はプランジャバレル、(2)は射出シリンダ、(5)はノズル、(6)はモータ、(7)はホツパである。また樹脂に十分な混練を与えるために、押出スクリュ00内で樹脂が環流するよう、同押出スクリュ00の先端に押出スクリュバレル00との間で、スロットル部02の隙間Fを構成する部分を設けてある。即ち、スクリュ先端及びスクリュ先端部を夫々スロットルバルブ状に加工してある。

さて第2図において可塑化時は、ホツパ(7)内の

樹脂は押出スクリュ00により溶融、搬送され、空間Eからスロットル部02の隙間Fを通り、プランジャバレル(1)の空間D、Cに貯えられる。樹脂の混練を良くするには、空間Eの樹脂圧を上げ、スクリュ00内での樹脂環流を発生させるのであるが、樹脂圧を調整するには、スクリュ00を軸方向に移動させてδを調整し、スロットル部02の隙間Fの抵抗を調整すればよい。

第2図ではモータ(6)とスクリュ00が一体になっており、スロットル部02の隙間Fを調整する為にモータ、スクリュ全体を軸方向に移動させる方式としてある。なお、図中03は射出プランジャ、04はチエツクリング、Aは射出シリンダ(2)の空間、Gは隙間である。

第3図及び第4図は第2図のスクリュ00の先端及びスクリュバレル00の先端部の拡大図で、スクリュ00を前、後進させることにより、スロットル部の隙間Fの長さを加減し、空間Eに発生する樹脂圧を制御せんとするもので、空間Eの樹脂圧を高くしようとする時には、第3図の如く隙間Fを

長く、反対に低くしようとする時には第4図の如く隙間Fを短くすればよい。なお、スロットル部の半径方向の隙間及びスロットルの長さについての具体的な数値は、使用材料、成形製品などにより適宜選択できる。

以上詳細に説明した如く本発明は構成されているので、プランジャ隙間からの樹脂洩れや、金型内への樹脂の流れ込みを生ずることなしに、スクリュ背圧を押出機先端部で発生させることができ、可塑化時に樹脂に十分な混練効果を与えることができる。

4. 図面の簡単な説明

第1図は従来のプランジャブリブラ式射出成形機の側断面図、第2図は本発明の実施例を示すプランジャブリブラ式射出成形機の側断面図、第3図及び第4図は夫々作動位置を異にする第2図の押出スクリュ先端部の拡大図である。

図の主要部分の説明


- 1 … プランジャバレル
- 2 … 射出シリンダ

- 6 … モータ
- 10 … 押出スクリュ
- 11 … 押出スクリュバレル
- 12 … スロットル部
- 13 … 射出プランジャ
- E … 空間
- F … 隙間


特 許 出 願 人 三 菱 重 工 業 株 式 有 限 公 司
復代理人 弁理士 唐 木 貴




第1図




第2図



第3図



第4図



CLIPPEDIMAGE= JP359085729A

PAT-NO: JP359085729A

DOCUMENT-IDENTIFIER: JP 59085729 A

TITLE: PLUNGER PREPLASTICIZING TYPE INJECTION MOLDING MACHINE

PUBN-DATE: May 17, 1984

INVENTOR-INFORMATION:

NAME

ISHIKAWA, KOICHI

ASSIGNEE-INFORMATION:

NAME

COUNTRY

MITSUBISHI HEAVY IND LTD

N/A

APPL-NO: JP57195730

APPL-DATE: November 8, 1982

INT-CL_(IPC): B29F001/00

US-CL-CURRENT: 425/149

ABSTRACT:

PURPOSE: To enable the back pressure of a screw to be freely adjustable by making the screw to be movable in the axial direction, while forming the gap of a throttle part in the space between the screw and a barrel at the tip of an extruding screw.

CONSTITUTION: So as to circulate resin in an extruding screw 10, the part where the gap F of a throttle part 12 is formed, is provided at the tip of said extruding screw 10 between the screw and an extruding screw-barrel 11. That is, the screw tip and screw tip portion are respectively machined to the shape of a throttle valve. In resin plasticizing process, resin is molten and carried by the extruding screw 10, and then the resin is kept in the spaces D, C of a plunger barrel 1 through the gap F of the throttle part 12 from the space E. The regulation of the screw pressure is performed by controlling the resistance of the gap F of the throttle part 12, while regulating Δ by moving the screw 10 in the axial direction.

COPYRIGHT: (C)1984,JPO&Japio

(Translation of Laid Open Sho 59-85729)

(19) Japanese Patent Office (JP)

(11) Laid Open Patent Publication No. Sho 59-85729

(12) Laid Open Patent Publication (A)

(43) Date of publication: May 17, 1989

(51) Int. Cl.³

Domestic
Classification
Symbol

Identification No.

B29F 1/00

8016-4F

Number of Claim: 1

Request for examination:

not yet filed

(Total 3 pages)

(54) Title of the invention:

Plunger preplasticating type
injection molding machine

(21) Application No.:

Sho 57-195730

(72) Filing Date:

November 8, 1982

(72) Inventor:

Koichi Ishikawa

c/o Nagoya Kiki Seisakusho,
Mitsubishi Heavy Industries, Ltd.
1, Aza-Takamichi, Iwatsuka-cho,
Nakamura-ku, Nagoya-shi

(71) Patent Applicant:

Mitsubishi Heavy Industries, Ltd.

5-1, Marunouchi 2-chome, Chiyoda-ku,
Tokyo, Japan

(74) Sub Attorney:

Takao Karaki, Patent Attorney
(and one other)

Specification

1. Title of the Invention Plunger preplasticating type
 injection molding machine

2. Claim

A plunger preplasticating type injection molding machine characterized in that a gap of a throttle part is provided at a tip of a screw and at a tip part in a screw barrel in an extruder unit for the injection molding machine to build up a screw back pressure at the tip part in an extruder, and that means for moving the screw in an axial direction is provided to enable the screw back pressure to be controlled.

3. Detailed Description of the Invention

In order to sufficiently mix a resin to be plasticized, a certain pressure (a pressure of about $0 \sim 300 \text{ kg/cm}^2$) is built up in the resin locating at the tip in an extruder in some cases. When the pressure is built up, the hydraulic pressure in an injection cylinder 2 has been usually controlled so that the pressure in a plunger barrel 1 in Fig. 1 is increased.

Explanation of the operation will be made with respect to Fig. 1. A material in a hopper 7 is plasticized and conveyed by an extruding screw 9 in an extruding screw barrel 8, which is driven by a motor 6. In order to apply a screw back pressure to improve the kneading of the resin, it is enough to carry out plastication with a hydraulic pressure applied in a space A in the injection cylinder 2 at a slight magnitude. At the time, a pressure of $0 \sim 300 \text{ kg/cm}^2$ is built up at the tip of the extruding screw 9, in a stop valve 3 and in the plunger barrel 1. However, the conventional machine shown in Fig. 1 has creased the following problems. Specifically, there have been created problems, such as the occurrence of resin leakage at the stop valve 3 and at a gap between the injection plunger 4 and the plunger barrel 1 because of an increase in the resin pressure in the plunger barrel 1 during plastication, and an obstacle to molding in a next cycle in a fully automated operation because

of inflow of the resin into a mold in the absence of the function as the stop valve 3 in a nozzle when the mold is opened during plastication.

The present invention is proposed to solve the problems of the conventional machine. It is an object of the present invention to sufficiently knead a resin by building a screw back pressure without causing resin leakage or the inflow of the resin into a mold, and to provide a plunger preplasticating type injection molding machine wherein a screw and a tip of a screw barrel are formed in such a shape to have a throttle valve structure to build up a screw back pressure at a tip portion in an extruder and to produce a pressure, and wherein the screw is movable in an axial direction to enable the screw back pressure to be arbitrarily controlled.

Now, an embodiment of the present invention will be described, referring to the drawings. Fig. 2 shows the embodiment of the present invention, wherein reference numeral 1 designates a plunger barrel, reference numeral 2 designates an injection cylinder, reference numeral 5 designates a nozzle, reference numeral 6 designates a motor, and reference numeral 7 designates a hopper. In order that a resin is circulated in an extruding screw 10 to be sufficiently kneaded, the extruding screw 10 has a tip provided with a part forming a gap F for a throttle part 12 between an extruding screw barrel 11 and the tip. In other words, each of the tip of the screw and the tip part of the screw is machined into a throttle valve shape.

Referring to Fig. 2, the resin in the hopper 7 is molten and conveyed by the extruding screw 10, passes through the gap F of the throttle part 12 from a space E, and is accumulated in spaces D, C in the plunger barrel 1 during plastication. In order to improve the kneading of the resin, the resin pressure in the space E is increased, causing the resin to circulate in the screw 10. In order to control the resin pressure, the screw 10 may be moved in an axial direction to adjust δ , modifying the resistance in the gap F of the throttle part 12.

In Fig. 2, the screw 10 is integral with the motor 6, and there is adopted a system wherein the screw and the motor are moved in the axial direction as a whole to control the gap F of the throttle part 12. In this figure, reference numeral 13 designates an injection plunger, reference numeral 14 designates a check ring, symbol A designates a space in the injection cylinder 2, and symbol G designates a gap.

Fig. 3 and Fig. 4 are enlarged views of the tip of the screw 10 and the tip part of the screw barrel 11 shown in Fig. 2. The screw 10 can be moved back and forth to increase and decrease the length of the gap F of the throttle part, controlling the resin pressure built up in the space E. When the resin pressure in the space E is raised, the gap F is increased as shown in Fig. 3. When the resin pressure is reduced, the gap F is decreased as shown in Fig. 4. Specific values about the gap of the throttle part in a radial direction and the length of the throttle may be properly determined, depending on the material used, a molded product and so on.

16 { Since the present invention is constructed as explained in detail,
the present invention can build up the screw back pressure at the tip part in
an extruder to provide a resin with a sufficient kneading effect during
plastication without the resin leaking through a plunger gap or the resin
20 { flowing into a mold.

4. Brief Explanation of the Drawings

Fig. 1 is a cross-sectional view of a conventional plunger preplasticating type injection molding machine in an axial direction; Fig. 2 is a cross-sectional view of the plunger preplasticating type injection molding machine according to an embodiment of the present invention; and Fig. 3 and Fig. 4 are enlarged views of the tip part in the extruding screw of Fig. 2, which are different in terms of working position.

Explanation of Essential Parts in the Drawings

- 1 Plunger barrel
- 2 Injection cylinder
- 6 Motor
- 10 Extruding screw
- 11 Extruding screw barrel
- 12 Throttle part
- 13 Injection plunger
- E Space
- F Gap

Patent Applicant: Mitsubishi Heavy Industries, Ltd.

Sub Attorney: Takao KARAKI